



UNIVERSITI PUTRA MALAYSIA

**DEVELOPMENT OF MnZn FERRITE AS A TRANSFORMER CORE
MATERIAL FOR SWITCH-MODE POWER SUPPLIES (SMPS)**

MASDHIAH MASPOL

FSAS 2001 5

**DEVELOPMENT OF $MnZn$ FERRITE AS A TRANSFORMER CORE
MATERIAL FOR SWITCH-MODE POWER SUPPLIES (SMPS)**

MASDHIAH MASPOL

**MASTER OF SCIENCE
UNIVERSITI PUTRA MALAYSIA
2001**



**DEVELOPMENT OF $MnZn$ FERRITE AS A TRANSFORMER CORE
MATERIAL FOR SWITCH-MODE POWER SUPPLIES (SMPS)**

By

MASDHIAH MASPOL

**Thesis Presented in Fulfilment of the Requirement for the Degree of Master of
Science in the Faculty of Science and Environmental Studies
Universiti Putra Malaysia
July 2001**



Abstract of the thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Master of Science.

DEVELOPMENT OF MnZn FERRITE AS A TRANSFORMER CORE MATERIAL FOR SWITCH-MODE POWER SUPPLIES (SMPS)

By

MASDHIAH MASPOL

July 2001

Chairman: Associate Prof. Mansor Hashim, Ph.D.

Faculty: Science and Environmental Studies

In electronics, magnetic transformer using ferrite cores are widely applied. In the recent years the rapid growth in popularity of Switched Mode Power Supplies (SMPS) units has led to a corresponding demand for high frequency ferrite cored power transformer. The main motivation for using ferrite transformer cores is the dramatic reduction of eddy current losses when compared with traditional iron core transformer. This study has been carried out to improve processing and understand the loss mechanisms of manganese zinc (MnZn) ferrite to meet the SMPS requirements.

The preparation of the samples was typical for MnZn ferrite production utilizing wet method technique. The experimental work was divided into three parts namely the effect of composition, the effect of atmosphere control and the effect of additives.

The effect of composition showed that MnZn ferrite sample with chemical composition of $(\text{MnO})_{0.335}(\text{ZnO})_{0.130}(\text{Fe}_2\text{O}_3)_{0.535}$ yield high initial permeability, μ_i values. The effect of controlling of the sintering atmosphere with the same composition did not achieve the desired result. μ_i dropped and Relative Loss Factor decreased. The effect of additives showed that In_2O_3 addition suppressed grain growth and V_2O_5 cause duplex structure, which is the main reason, the μ_i declined.

This can be concluded that to improve the magnetic characteristics is by controlling the microstructure by having an appropriate and proper controlling sintering scheme.

**Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk ijazah Master Sains.**

**PENGHASILAN FERIT $MnZn$ UNTUK TERAS TRANSFORMER BAGI
BEKALAN KUASA MOD SUIS (BKMS)**

Oleh

MASDHIAH MASPOL

Julai 2001

Pengerusi: Prof. Madya Mansor Hashim, Ph.D.

Fakulti: Sains dan Pengajian Alam Sekitar

Di dalam bidang elektronik, penggunaan teras transformer daripada bahan ferit telah diaplikasikan secara meluas. Pada tahun-tahun kebelakangan ini pertumbuhan mendadak oleh penggunaan Bekalan Kuasa Mod Suis (BKMS) telah menyebabkan permintaan yang tinggi dalam menghasilkan transformer berfrekuensi tinggi. Motivasi utama ialah transformer ferit mampu mengurangkan kehilangan tenaga disebabkan arus pusar jika dibandingkan dengan transformer yang diperbuat daripada besi. Kajian ini dijalankan bertujuan memperbaiki kaedah pemprosesan dan mengkaji mekanisme kehilangan bagi memenuhi ciri-ciri yang diperlukan oleh mangan zink ($MnZn$) ferit bagi SMPS.

Penyediaan sampel-sampel $MnZn$ ferit ialah dengan kaedah basah. Eksperimen yang dijalankan terbahagi kepada tiga bahagian iaitu kesan komposisi, kesan pengawalan atmosfera persinteran dan kesan bahan tambah.

Keputusan menunjukkan bahawa dengan sampel MnZn ferit berformula kimia $(\text{MnO})_{0.335}(\text{ZnO})_{0.130}(\text{Fe}_2\text{O}_3)_{0.535}$ memberikan nilai ketelapan awal, μ_i yang tinggi. Walaubagaimanapun kesan pengawalan atmosfera persinteran bagi sampel yang sama tidak menunjukkan hasil yang dikehendaki. μ_i menurun begitu juga dengan kehilangan. Kesan penambahan Indium menyekat pertumbuhan butiran manakala Vanadium menyebabkan kesan Dupleks yang menjadi sebab utama μ_i menurun.

Dengan ini dapat disimpulkan bahawa untuk memperbaiki hasil yang dikehendaki ialah dengan mengawal mikrostruktur melalui pengawalan kitaran persinteran yang sesuai dan betul.

ACKNOWLEDGEMENTS

First and foremost, I would like to extend my deepest praise to Allah s.w.t that has given me strength, determination and courage to complete my project.

I would like to extend my gratitude and indebtedness to my supervisor, Associate Professor Dr. Mansor Hashim for giving me this path to pursuit my knowledge of this technological ferrites. I would also like to express my sincere appreciation to Dr. Jumiah Hassan, Dr. Jamil Suradi and Dr. Azmi Zakaria for their valuable comments and suggestions of my work in this thesis.

I would like to thank the following person from Chemistry Department, En. Kamal Margona, En. Ismail Yassin and En. Abas Abdul Rahman for their kind assistance in apparatus set-up. I also wish to thank the staff from Physics Department who had rendered their help in various ways during my research work.

A special thanks goes to all my friends for their help, advice and support. Last but not least, to my family especially my parents for their loving and prayers in making this report succeed.



I certify that an Examination Committee met on 31st July 2001 to conduct the final examination of Masdhiah Maspol on her Master of Science thesis entitled “Development of MnZn Ferrite as a Transformer Core Material for Switch-Mode Power Supplies (SMPS)” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulation 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

JUMIAH HASSAN, Ph.D.
Faculty of Science and Environmental Studies
Universiti Putra Malaysia
(Chairperson)

MANSOR HASHIM, Ph.D.
Associate Professor
Faculty of Science and Environmental Studies
Universiti Putra Malaysia
(Member)

JAMIL SURADI, Ph.D.
Faculty of Science and Environmental Studies
Universiti Putra Malaysia
(Member)

AZMI ZAKARIA, Ph.D.
Faculty of Science and Environmental Studies
Universiti Putra Malaysia
(Member)



MOHD. GHAZALI MOHAYIDIN, Ph.D.
Professor/Deputy Dean of Graduate School
Universiti Putra Malaysia

Date: 29 SEP 2001

This thesis submitted to the Senate of Universiti Putra Malaysia has been accepted as fulfilment of the requirement for the degree of Master of Science.




AINI IDERIS, Ph.D
Professor
Dean of Graduate School
Universiti Putra Malaysia

Date:

08 NOV 2001

DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations, which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.



MASDHIAH MASPOL

Date: 19 / 9 / 2001

TABLE OF CONTENTS

	Page
ABSTRACT	ii
ABSTRAK	iv
ACKNOWLEDGEMENTS	vi
APPROVAL SHEETS	vii
DECLARATION	ix
LIST OF TABLES	xii
LIST OF FIGURES	xiii
LIST OF PLATES	xv
LIST OF SYMBOLS AND ABBREVIATIONS	xvi
CHAPTER	
I INTRODUCTION	1
SMPS in General	1
Transformer as a Component of SMPS	1
Basis of Work	2
Statement of Objectives	3
II LITERATURE REVIEW	5
Introduction.....	5
Past Study	5
Properties Control	6
The Effect of Additives	7
The Effect of Indium Oxide Addition	7
The Effect of Vanadium Oxide Addition	7
III THEORY	9
Introduction	9
Crystal Structure of Ferrites	9
The Origin of Magnetism in Ferrites	14
Some Aspects of MnZn Ferrites	16
Initial Permeability	16
Magnetic Losses	17
Hysteresis Characteristics	19
Resistivity	21
Curie Temperature, T_c	22
Microstructural Aspects	23
IV EXPERIMENTAL PROCEDURES	27
Introduction	27
Sample Preparation	27



	Raw Materials	27
	Weighing and Mixing	28
	Calcining	28
	Grinding	29
	Granulation	29
	Forming	30
	Sintering	30
	Measurement Techniques	33
	Initial Permeability, μ_i and Relative Loss Factor, $\tan\delta/\mu_i$	33
	Hysteresis Parameters	34
	Resistivity	36
	Curie Temperature, T_c	37
	Density	37
	Microstructure Analysis	38
	Estimation of Errors	39
V	RESULTS AND DISCUSSION	41
	Introduction	41
	The Effect of Increasing Mn and Reducing Zn	41
	The Effect of Sintering Condition	44
	The Effect of Increasing Fe and Reducing Zn	53
	The Effect of Indium Addition	55
	The Effect of Vanadium Addition	59
	Conclusions	62
	Suggestions	63
	BIBLIOGRAPHY	64
	VITA	67

LIST OF TABLES

Table	Page
3.1 Cation distribution in a unit cell of MO. Fe ₂ O ₃	11
3.2 Crystallographic data for some spinel ferrites	12
3.3 Site preference of the cations involved in MnZn spinel ferrite	12
3.4 List of the resistivities of several ferrites	22
4.1 Measured parameters with errors (in percentages)	40
5.1 Mole fraction values for MnZn ferrite first series samples	41
5.2 Comparison of some properties of MnZn ferrite samples prepared in the laboratory with sample from industry	52
5.3 Mole fraction values for MnZn ferrite second series sample	53
5.4 Properties measured for second series sample of MnZn ferrite	54
5.5 Density and resistivity values of MnZn ferrite samples for different amount of V ₂ O ₅	61



LIST OF FIGURES

Figure	Page
2.6 A unit cell of the ferrite spinel structure. (Two octants of the spinel unit cell; A ions are on tetrahedral sites and B ions on octahedral sites of the Oxygen anion packaging)	10
3.2 Schematic diagram of super-exchange interaction in ferrites	15
3.3 Schematic hysteresis loop illustrating the primary magnetic quantities; The saturation magnetization, B_s , remanent induction, B_r and coercive force, H_c	20
3.4 Permeability of a MnZn ferrite as a function of grain size in microns, from Guillaud, 1956	25
3.5 The initial permeability of a nickel-zinc ferrite as a function of average grain diameter (1) together with an indication of the percentage of crystallites found to contain visible pores (2) (Guillaud, 1957)	25
4.1 Schematic diagram of apparatus set-up during sintering procedure	31
4.2 Equilibrium weight changes as oxygen as a function of atmospheric oxygen content and temperature for the system: $(\text{MnO})_{0.268}(\text{ZnO})_{0.183}(\text{Fe}_2\text{O}_3)_{0.549}$	32
4.3a Basic configuration circuit of hysteresis curve characteristic measurement	35
4.3b Hysteresis loop with V_{Bs} , V_{Br} and V_{BHc} measured from the oscilloscope	36
4.3c Radius, r and cross sectional area, A for toroidal sample	36
4.4 The procedure in analyzing microstructure of the sample	38
5.1 Graph of initial permeability of MnZn Ferrite samples measured at frequency 10 kHz	43
5.2 Graph of Relative Loss Factor of MnZn Ferrite samples measured at frequency 10 kHz	43
5.3 The X-ray diffraction pattern of MnZn ferrite sample sintered in : a) Air and b) $\text{O}_2\text{-N}_2$ atmosphere ($I = \alpha\text{-Fe}_2\text{O}_3$)	46

5.4	Plot of initial permeability, μ_i against frequency of MnZn ferrite samples for different sintering conditions	47
5.5	Plot of RLF against frequency of MnZn ferrite samples for different sintering conditions	49
5.6	Plot of permeability Vs temperature of MnZn ferrite sample sintered in: a) Air and b) O ₂ -N ₂ atmosphere.....	51
5.7	Variation of initial permeability and relative loss factor of MnZn ferrite samples with different weight % addition of In ₂ O ₃ measured at frequency 10 kHz	55
5.8	Plot of density against different amount of In ₂ O ₃	58
5.9	Plot resistivity against different amount of In ₂ O ₃	58
5.10	Variation of initial permeability and Relative Loss Factor with different weight % addition of V ₂ O ₅ onto MnZn ferrite samples measured at frequency 10 kHz	59

LIST OF PLATES

Plate	Page
5.1 Microstructure of MnZn ferrite sample sintered in: a) air and b) O ₂ -N ₂ atmosphere.....	45
5.2 Microstructure of MnZn ferrite sample with In ₂ O ₃ addition: a) 0.50 wt% and b) 1.00 wt%	56
5.3 Microstructure of MnZn ferrite sample with addition of V ₂ O ₅ : a) 0.01 wt% and b) 0.05 wt %.....	60



LIST OF SYMBOLS AND ABBREVIATIONS

A	cross sectional area, cm ²
a ₀	grain diameter, microns
AC	alternating Current
B _s	saturation magnetization
B _r	remanent induction, remanence
d	density (g/cm ²)
DC	direct current
Do	outer diameter
Di	inner diameter
f	frequency (Hertz)
Fe	iron
H _c	coercive force
In	indium
K	temperature, Kelvin
L _p	parallel inductance
Mn	manganese
N ₂	nitrogen
N _p	number of turns in primary winding
N _s	number of turns in secondary winding
n	number of unpaired electrons in an atom
Oe	oersted
O ₂	oxygen

PO_2	oxygen partial pressure
PVA	polyvinyl alcohol
Q	quality factor
R	resistance
RLF	relative loss factor
SEM	scanning electron microscopy
SMPS	switch-mode power supply
T_c	curie temperature
μ_0	permeability of free space
μ_i	initial permeability
μ'	real permeability
μ''	imaginary part of permeability
ρ	resistivity, Ohm-cm
XRD	x-ray diffraction
Zn	zinc

CHAPTER 1

INTRODUCTION

SMPS in General

The so-called Switch-Mode Power Supply (SMPS) is a class of power supply that is made up of switching stages to process electric power.

Switched Mode Power Supplies may have the combination of capacitor, filter (electromagnetic interference suppressor), rectifier, transformer, choke, diode and transistor to operate. Transformer core material was the object of study in this research.

Transformer as a Component of SMPS

The power transformers that transform the high frequency input voltage to the usable voltage are at the heart of the SMPS system. The transformer is required to transform (reduce or increase) the mains AC voltage to a level that is better suited to the desired DC output voltage level and to provide electrical isolation between the input and output of the power supply.

Since 1970s, the 50 Hz linear power transformers with iron cores have been gradually replaced by low conductive ferrite. In this way a considerable size reduction of the magnetic core was realized to operate at higher frequencies. It was not until the 1980's that the advent of transistor-switched power supplies created a need for a ferrite material operating at much higher flux levels. The frequency range for early power ferrite was 16-25 kHz. During 1980-1984, the Switched-Mode Power Supply market grew very rapidly as did for power ferrite transformer. Now power supplies operating at 1 MHz and above are commercially available.

Basis of Work

In this project, MnZn ferrites has been selected as a material of study in the fabrication of transformer core for SMPS application because in power application, materials with large magnetic moments are needed. The magnetic metal ions with the most unpaired spins are chosen. Mn with electron configuration ($[\text{Ar}] 3d^5$) gives MnZn ferrites $5\mu_B$ which is the highest magnetic moment measured among other ferrites. With this characteristic, MnZn ferrite has the ability to conduct high amplitude permeability, which is one of SMPS requirement other than high saturation flux density and low magnetic losses. The limitation of MnZn ferrites application at higher frequencies is because of its eddy current losses.

Because of the easy exchange valence ions, fabrications of MnZn ferrites need a very complicated task especially in the sintering process. The problem encountered is a strict control of oxygen partial pressure while sintering; during soaking period and cooling cycle, because any non-equilibrium during this process will cause zinc losses and $\alpha\text{-Fe}_2\text{O}_3$ precipitation together with $\beta\text{-Mn}_2\text{O}_3$, which cause inhomogeneities and stresses that will affect the desired magnetic properties.

Statement of Objectives

The objective of this project is to investigate whether varying the metal cations in a chemical composition, changing the sintering condition and study the effect of additives onto a MnZn ferrite specimens could improve a material having high magnitude of permeability and the reduction of the specific magnetic losses through the characterization of magnetic, electrical and microstructure properties.

The aim of this study is to obtain a MnZn ferrite properties appropriate for transformer for SMPS application, utilizing our scientific knowledge in Solid State Science and to have a reproducible material for industrial needs.

In this report, five chapters will be presented. A very general outline of this study to be carried out has been given. In Chapter II we will review some of the past results, which is relevant and be a helpful reference to the project. The basic theory for spinel ferrite and measurement involved will be given in Chapter III and the experimental details will be described in Chapter IV. The results obtained and conclusions will be discussed and presented in Chapter V.

CHAPTER II

LITERATURE REVIEW

Introduction

Since the need of transformer to be high permeability, any relevant studies that relate to this matter will be reviewed. The study of technique to be used and some results of the effect of Indium and Vanadium addition that will be helpful reference in this research will be given in this chapter.

Past Study

Other compositions of ferrites like NiZn and MgZn ferrite are usually sintered in air. Economos (1955) was the first who investigate effects of firing atmosphere of manganese ferrite. MnZn ferrites need a strict control of atmosphere during firing, because one reason is of the variable ion valency. In MnZn ferrite, the oxygen diffusion rates are still rapid enough during the first stages of the cool. It is still possible at that stage to control the oxidative state through the atmosphere to ensure that properties are not be destroyed by further oxidation or reduction during the cooling period. As it is further cooled, the possibilities of equilibration are reduced

with the decreased diffusion rates. Thus a well controlled oxygen partial pressure (P_{O_2}) in a Nitrogen (N_2) atmosphere is required.

This will refer to an equilibrium phase diagram of a MnZn ferrite shows a weight changes with oxygen as a function of atmosphere oxygen content and temperature for the system of $(MnO)_{0.268}(ZnO)_{0.183}(Fe_2O_3)_{0.549}$ (Slick, 1971). The diagram shows the importance of atmosphere on the oxidation state in the spinel phase and the hematite phase boundary. From this diagram, cooling will be exercise along an iso-composition line and then quickly cooling through the phase boundary at the lowest temperature when the kinetic are sluggish. This figures agrees well with the universal equilibrium atmosphere diagram first shown by Blank (1961) and working more detail by Morineau and Paulus (1975).

Properties Control

A several studies by researchers to improve properties of MnZn ferrites have been made. (Michalowsky et al, 1993) indicate that to gain high quality of MnZn ferrite, a precise control of the microstructure is required especially the grain size distribution, the chemical composition and the grain interfaces or grain boundaries.

(Rosales et al , 1995) found that to prepare high permeability of MnZn ferrites is very complicated task that homogeneity must be carefully monitored. It refers to the stoichiometry of composition through the whole specimen.